PREMIUM
ROOFING PRODUCTS

01992 444 100

enquiries@leadsales.co.uk

PRODUCT INFORMATION SHEET

WOOD CORED ROLL



Lead Wood Cored Roll



Lead King Roll



Zinc Batten Roll



Zinc King Batten Roll

Recommended by the Lead Sheet Advisory Service (LSAS)

- Lead Wood Roll is for lead sheet joints with the fall on flat or pitched roofs.
- Zinc Wood Roll is for shallow pitched hard metal roofs.
- Recommended for areas where ponding or storm flooding is possible.
- Resistant to damage by foot traffic.
- Forms aesthetically pleasing joint.

Premium Wood Cored Rolls and Zinc Batten Rolls are used as a basis for lead sheet joints on flat roofing and pitched roofing, as well as traditional hard metal roofing. When there is the prospect of foot traffic, the wood cored roll joint is preferable to a hollow roll joint, as it is less prone to pressure damage.

Premium Wood Cored Rolls have been subjected to high pressure impregnation of a wood preservative, which protects the wood against timber rotting fungi and wood destroying insects.

Premium Wood Cored Rolls are unsuitable for use on curves surfaces such as semi-circular dormer tops.

LSAS
LEAD SHEET ADVISORY SERVICE

Unit B, Bingley Road, Hoddesdon,
Hertfordshire, EN11 0NX

PREMIUM ROOFING PRODUCTS

01992 444 100 enquiries@leadsales.co.uk

PRODUCT INFORMATION SHEET

- Fix a suitable length of Premium Wood Cored Roll to the substrate using 75mm stainless-steel screws at 450mm centres.
- Any exposed cut surfaces will need to be re-treated. Roll ends cut to about 45°.
- Turn the lead sheet undercloak three quarters around the wood cored roll and fix the lead sheet using copper or stainless steel annular ring shank nails. Fixing only the top third of the lead bay leaving the bottom two-thirds of the sheet free to expand and contract.
- Dress the overcloak over the roll, extending 40mm over the far side of the rolls as a splash lap. This serves to stiffen the free edge and keep it in position.
- For hard metal roofs, use suitable preformed zinc cappings.

LOT SIZES

Lead Wood Roll:
50mm (w) x 2.4m (l)

Lead King Roll:
75mm (w) x 2.4m (l)

Zinc Wood Roll:
38mm (w) x 2.4m (l)
50mm (w) x 2.4m(l)

Zinc King Roll:
75mm (w) x 2.4m (l)

HEALTH & SAFETY ADVICE

- Treated timber may be handled without special precautions, other than observing standard hygiene procedures.
- If timber must be cut or worked, avoid inhalation of dust from saws or mechanical sanders.
- Dispose of treated timber waste through an authorised waste contractor; do not use as domestic fuel, anima bedding or litter.
- When working with lead, follow standard health and safety procedures as laid out in Control of Lead at Work Regulations 2002. Always wash hands well before eating, drinking or smoking
- Remove lead residues from skin after working with lead metal by washing with soap and bodywash.

PRODUCT DESCRIPTION & PROPERTIES

Composition: Preservative is applied to treated timber by high pressure impregnation.

Appearance: Treated timber is greenish in appearance.

Preservatives: Osmose Celcure A0 - containing copper, chromium and arsenic oxides, or Osmose Celcure AC500 - containing copper salts, an organic co-biocide and boric acid.

Unit B, Bingley Road, Hoddesdon, Hertfordshire, EN11 0NX